


TORAYFAN® PWS3

Application

- Confectionnary
 - Food
 - Snacks
 - Bakery
- Industrial



METALLIZED BOPP FILM
LOW SIT SEALABLE LAYER

Benefits

- Super moisture barrier
- Excellent hot tack and very wide heat seal range
- Non craze metal surface
- Bright foil appearance
- Excellent bondering in extrusion and adhesive laminations

Typical Values *

Properties	Test Method	Unit	15 μ m	17,5 μ m
Nominal Yield		m ² /kg	73	62,6
Tensile Strenght @ Break MD	ASTM D 882	daN/mm ²	15	15
Tensile Strenght @ Break TD			30	30
Young's Modulus MD	ASTM D 882	daN/mm ²	220	220
Young's Modulus TD			400	400
Elongation @ Break MD	ASTM D 882	%	200	200
Elongation @ Break TD			50	50
Dimensional Stability MD	Internal Method	%	8	8
Dimensional Stability TD			4	4
OF (sealant to sealant)	ASTM D1894		0,6	0,6
Hot Tack @ 121°C	Internal Method	N/25mm	3	3
Heat-seal Strenght @121°C	Internal Method	N/25mm	3,5	4
SIT (>2N/25mm)	Internal Method	°C	85	85
OTR @23°C, 0% RH	ASTM D3985	cc/m ² /day	50	50
MVTR, 90% HR, 38°C	ASTM F1249	g/m ² /day	0,15	0,15

Regulation

Toyrafan® PWS3 complies with European applicable requirements for food contact applications. For Toray's certification concerning specific applications with each product, please refer to the 'Declaration of Compliance'.

Presentation of the rolls

Roll packaging: The rolls are suspended on standard paper core with internal diameter of 152.8mm. For all presentation, minimum roll width = 340mm and maximum roll width = 2450mm.

Returnable packaging: Wooden flanges, plastic flanges and pallets are returnable. The metallized side is identified on the labels.



Please contact us for...

- Any other presentation (width, length, core)
- Process for returnable packaging
- Any other information about typical values, measuring conditions, tolerances, deliveries...

* These values do not constitute binding specifications

Torayfan® is a registered trademark of Toray Film Europe SAS- TFE January 2018

DISCLAIMER: This leaflet is provided for informational purpose only and is not binding, nor can it constitute specifications to the buyer. The information contained in this document is based on numerous tests and trials we have carried out in our laboratories. Deviations from the results thus obtained can therefore be experienced depending on the actual conditions of use. This document does not provide any guarantee with regard to compliance of our product with the typical values indicated, nor does it provide any guarantee as the suitability of our products for any particular use.