


TORAYFAN® PHS3

Application

ConfectionerySnacks

• Suitable for adhesive lamination



METALLISED BOPP FILM WITH LOW SIT SEALABLE LAYER

Benefits

- Good moisture barrier
- Excellent hot tack and very wide heat seal range
- Bright foil appearance



Toray Films Europe SAS Place d'Arménie 01700 Saint-Maurice-de-Beynost FRANCE

Typical Values (These values do not constitute binding specifications)

Properties	Test Method	Unit	15 µm	17.5 μm	20 µm
Nominal Yield		m²/kg	73.3	62.6	54.8
Tensile Strength @ Break MD	ASTM D 882	daN/mm²	15	15	15
Tensile Strength @ Break TD	-		30	30	30
Young's Modulus MD	ASTM D 882	daN/mm²	220	220	220
Young's Modulus TD	-		400	400	400
Elongation @ Break MD	ASTM D 882	%	200	200	200
Elongation @ Break TD	-		50	50	50
Heat Shrinkage MD	Internal Method	%	8	8	8
Heat Shrinkage TD	-		4	4	4
COF (sealant to sealant)	ASTM D1894		0.6	0.35	0.4
Heat-seal Strength @121°C	Internal Method	N/25mm	3.5	4.2	3
SIT (>2N/25mm)	Internal Method	°C	85	85	85
OTR, 0% HR, 23°C,	ASTM D3985	cc/m²/day	50	50	40
MVTR, 90% HR, 38°C	ASTM F1249	g/m²/day	0.3	0.3	0.3

Regulation

Torayfan[®] PHS3 complies with European applicable requirements for food contact applications. For Toray's certification concerning specific applications with each product, please refer to the 'Declaration of Compliance'. Torayfan[®] PHS3 is phtalate free.

Presentation of the rolls

Roll packaging: The rolls are suspended on standard paper core with internal diameter of 152.8mm. For all presentation, minimum roll width = 340mm and maximum roll width = 2450mm.

Returnable packaging: Wooden flanges, plastic flanges and pallets are returnable. The metallised side is identified on the labels.



Please contact us for...

- Any other presentation (width, length, core)
- Process for returnable packaging
- Storage & handling conditions
- Any other information about typical values, measuring conditions, tolerances, deliveries...

Torayfan® is a registered trademark of Toray Films Europe SAS - TFE July 2020

DISCLAIMER: This leaflet is provided for informational purpose only and is not binding, nor can it constitute specifications to the buyer. The information contained in this document is based on numerous tests and trials we have carried out in our laboratories. Deviations from the results thus obtained can therefore be experienced depending on the actual conditions of use. This document does not provide any guarantee with regard to compliance of our product with the typical values indicated, nor does it provide any guarantee as the suitability of our products for any particular use.